

## 940nm 60mW VCSEL Diode

### VD-0940C-060M-XA-2A0

#### Features

- Single wavelength
- Low wavelength drift
- Oxide isolation technology
- Low threshold current
- High reliability
- Easy to collimate

#### Applications


- 3D sensors
- Lidars
- IR illuminations
- Medical applications
- Proximity sensors

#### PRODUCT IDENTIFY

Part Number	Description
VD-0940C-060M-XX-2A0	940nm 60mW VCSEL Diode

#### CODE RULES:

VD-0940C-060M - X X - 2 A 0



- Annex, 0
- Product version, A
- Accessories, CW mode = 2
- Package type, A=2016, C=3535, E=7060
- Substrate, 1=AlN, 3=Cu/Ag
- Power units, M =milliwatts, W=watts, K=kilowatts
- Power value, 60
- Classification, Consumable
- Wavelength, 940nm
- Product classification, **VCSEL Diode**

#### I. Absolute maximum ratings

Parameter	Symbol	Rating	Unit
Case Operating Temperature	Top	-25 to 60	°C
Storage Temperature	Tsto	-40 to 85	°C
Reflow Soldering Temperature	Tsdr	260°C(10s)	°C
Reverse Voltage	Vr	5	V
Maximum Continuous Current	Imax	100	mA
ESD exposure (Human body) model	ESD	1K	V

#### Note:

1. Stresses greater than those listed under “Absolute Maximum Ratings” may cause permanent damage to the device. This is a stress rating only and functional operation of the device at these

or other conditions above those indicated in the operations section for extended periods of time may affect reliability.



2. In its maximum rating diode laser operation could damage its performance or cause potential safety hazard such as equipment failure.
3. Electrostatic discharge is the main reason for the laser fault of the diode. Take effective precautions against ESD. When dealing with laser diodes, use the wrist strap, grounding work surface and strict antistatic technology.

## II. Optical-electrical characteristics @25°C

Parameters	Conditions	Symbol	Unit	Min.	Typ.	Max.
Optical Power	$I_F=88\text{ mA}$	$P_o$	mW	-	60	-
Threshold Current	-	$I_{TH}$	mA	-	10	-
Forward Current	-	-	mA	-	88	-
Power Conversion Efficiency		$\eta$	%	-	30	32
Slope Efficiency	-	-	mW/mA	-	0.77	-
Die Size	-	-	um	-	210 x 151	-
Peak Wavelength	$P_o=60\text{mW}$	-	nm	930	940	950
Laser Forward Voltage	$I_F=88\text{ mA}$	$V_F$	V	-	2.205	-
Series Resistance	$I_F=88\text{ mA}$	R	$\Omega$		7.45	-
Beam Angle	$I_F=88\text{ mA}$	-	Degrees	-	20	-
Wavelength Temp. Drift	$I_F=88\text{ mA}$	-	nm/°C	-	0.07	-
Substrate	AlN / CuAg					


**Note:** Electro-Optical Characteristic with a package or diffuser would require further evaluation. Values are based on limited sample size and estimated values.

## III. LIV Graph and Wavelength




### IV. Mechanical Schematics


#### VD-0940C-060M-1A-2A0 (Substrate AlN, 2016 packaging, unit: mm)



#### VD-0940C-060M-3A-2A0 (Substrate CuAg, 2016 packaging, unit: mm)



#### VD-0940C-060M -3E-2A0 (substrate Cu/Ag, 7060 packaging), unit:mm





### Storage precautions

Our products were sealed by aluminum foil bag attaching packed desiccant, they are moisture proof and anti-static. please handle these gently to avoid damage. At the same time, please be ready for storage and take some moisture-proof measures to keep VCSEL away from dampness that may causes reliability failure.

Before opening, VCSEL must be saved for at least 90 days below 30°C with 60% RH.

After opening, VCSEL must be kept in an environment that temperature lower than 30°C and humidity lower than 60% RH and used up within 24 hours. When the storage humidity reaches and exceeds 60%, the products must be dehumidified at 60 °C for more than 24 hours before use.

### Others

1. Please use solder paste to cure the laser diode.
2. Please make sure that the heat of VD has been completely conducted to metal shell, to avoid affecting the optical power output.
3. This VD can be only used in constant voltage and current.
4. Operating voltage and current, refer to the table in paragraph II.
5. Please do not aim the laser to people or animal.
6. You can observe the laser spot through an image monitoring equipment.
7. Please do not touch VD surface by naked hands or squeeze the sealant on VD surface, or it may cause wrong optical angle and distorted laser spot, even damage the VD.
8. Please use ceramic suction nozzle to suck on the VD, so as to avoid VD sticking to the nozzle.
9. Please add a 0.02 s blowing action after locating the laser diode to aluminum substrate.

### VIII. Revision history

Revision	Date	Description
V.01	2020/2/25	The first official edition (A, Dec/19)
V.02	2020/6/19	Update part name
V.03	2020/7/02	Update part name

\*\*Brightlaser reserves the right to make modification at any time due to improved design from time to time, the merit behind is in order to supply the best product possible.